



LUBINOL ATF DEXRON VI

AUTOMATIC TRANSMISSION FLUID.

Product Description

LUBINOL ATF DEXRON VI fluid is a low viscosity Automatic Transmission Fluid which is made with a special additive technology, optimized for a wide range of passenger car applications.

Application

LUBINOL ATF DEXRON VI is used in an extensive range of European, American and Asian passenger car service fill applications. Additionally it can be used in commercial vehicle applications and power steering, too.

Properties

LUBINOL ATF DEXRON VI affords following benefits:

- Exceptional oxidation behaviour
- Low viscosity for high fuel economy
- smoother shifts over a long period of time
- excellent anti-rust properties
- low foaming tendency

Specification / Recommendation

DEXRON VI

Aisin Warner AW-1
Aisin Warner AW F8FXX
Aisin Warner JWS 3324
Bentley P/N PY112995PA
BMW/Mini P/N 83 22 0 142 516
BMW/Mini P/N 83 22 0 397 114
BMW/Mini P/N 83 22 2 163 514 (BMW 8072 B)
Chrysler/Dodge/Jeep P/N 05127382AA
Chrysler/Dodge/Jeep P/N 68043742AA
Daimler / Mercedes MB 236.12, 236.14, 236.41
FIAT 9.55550-AV1
FORD/Lincoln/Mercury P/N XT-10-QLV [LV]
FORD/Lincoln/Mercury P/N XT-6-QSP or -DSP [SP]
GM/GMC/Opel/Saturn AW1
GM/GMC/Opel/Saturn P/N 88863400, 88863401
Honda/Acura DW-1
Honda 082000-9017 (ATF Type 3.1)
Hyundai/Kia NWS-9638 T-5

Hyundai/Kia P/N 040000C90SG
Hyundai/Kia SP-IV / SPH-IV
Jaguar Fluid 8432
JASO M315, Class 1A
Land Rover P/N TYK500050, LR0022460
Maserati P/N 231603
Mazda FW 6A EL, FW 6AX EL
Mazda FZ
Mercon LV
Mitsubishi ATF-J3
Mitsubishi SP-IV
Nissan/Infinity Matic-S
Porsche P/N 000 043 304 00
Saab P/N 93 165 147 - AW-1
Shell 3353, Shell 134, Shell 1375.4
Toyota/Lexus/Scion WS
VW/Audi G 052 533, G 055 005 (-A, A2)
VW/Audi G 055 540 (A2)
ZF Lifeguard 9

Nominal Values

LUBINOL ATF DX VI	Unit	Value	Method
Density at 15	kg/m ³	851	DIN 51 757
Colour		Red	Visual
Viscosity at 40°C	mm ² /s	28,10	DIN 51 562
Viscosity at 100°C	mm ² /s	5,70	DIN 51 562
Viscosity Index		150	DIN ISO 2909

Pourpoint	°C	-45	DIN ISO 3016
Flash Point	°C	212	DIN ISO 2592

Specification variations in these characteristics may occur the instructions of manufacturer must be regarded. Further informations to be available by MSDS.